

Product Name : Mercure MBT

Product Description : 2 – Mercaptobenzothiazole (MBT)

CAS No. : 149-30-4

Supply Form : Pale Yellow Powder

Technical specification :

Parameters	Specification			Reference Test Method	
	Units	Min	Max	ASTM	Finorchem
Melting Point					
1) Initial	°C	170.0	-	ASTM D 1519A	-
2) Final		175.0	-	ASTM D 1519A	-
LOD at 105°C for 2hrs	%w/w	-	0.50	ASTM D 4571	-
Ash Content at 760°C for 2hrs.	%w/w	-	0.30	ASTM D 4574	-
Fineness thought 100 mesh	%w/w	99.90	-	ASTM D 5461	-
Assay by titration (%)	%w/w	95.00	-	-	In house method
Oil Content	%w/w	1.0	2.0	-	In house method

Additional Information:

Methanol Insolubles (%)	1.5 Max.	ASTM D 4934
Specific gravity at RT	1.45 – 1.55	ASTM D 1817
Bulk Density (kg/m3)	450 – 550	In house method

: Open mouth HDPE fabric bag with paper on the outside 25 kgs.Net.

Storage Life: : Two years from date of production.

Storage conditions: : Keep cool and dry in original packaging.

Product Safety : Relevant safety data and references as well as the necessary hazard warning labels can be found in the safety data sheet.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.